

DESCRIPTION

LayFLEX Midsoft is a durable elastomere based on Polycaprolacton-Polyester. It was specially developed for industrial applications and is ideally suited for the production of elastic and damping components. The material is optimized for the FFF/FDM process in regards to thermal stability and better flow properties. The raw material is compliant according to the REACH- and RoHS-Standards.

FEATURES

- Good mechanical properties
- Excellent chemical resistance
- Free of silicone, softeners and oil
- Free of halogen
- UV-Resistant

PROPERTIES

TEST	METHOD	UNIT	VALUE
Tensile modulus (E-Modulus)	ISO 527-2/5A/500	MPa	40
Ultimate elongation	ISO 527-2/5A/500	%	475
Stress at break	ISO 527-2/5A/500	MPa	- (50%)
	ISO 527-2/5A/500	MPa	17 (100%)
	ISO 527-2/5A/500	MPa	30 (300%)
VICAT A (VST)	ISO 306	°C	110*
Melting temperature	ISO 3146-C	°C	190-220
Density	ISO 2781	g/cm³	1.19
Abrasion resistance	ISO 4649-A	mm³	25
Shore hardness	ISO 868	Shore	98A
Tear strength	ISO 34-1B	kN/m	170
Glass transition temperature		°C	-30
Compressive strength	DIN 53452	MPa	40
Permeability AIR	DIN 53380	g/50°C	450/-
Permeability N2	DIN 53380	g/50°C	330/1800
Permeability O2	DIN 53380	g/50°C	840/4500
Permeability CO2	DIN 53380	g/50°C	6500/1900
Permeability N2O	DIN 53380	g/50°C	12400/-
Poisson-ratio	acc. to Hencky		0.47

*Temperature resistance tested at a minimum wall thickness of 4 mm.

CERTIFICATIONS & ADDITIONAL INFORMATION



STORAGE AND SHELF LIFE

Store in a dry room at room temperature (18-27°C / 65-80°F). Keep out of direct heat and sunlight. When stored correctly, this material has a shelf life of 2 years.

1. Additional info in our regulatory, additional information and chemical resistance data sheets.
2. Certifications depend on colors in final product. More info in the additional information sheet.



TEMPERATURE RESISTANCE **8**



EASE OF PRINTING **6**



VISUAL QUALITY **7**



LAYER ADHESION **10**



IMPACT RESISTANCE **10**



MAXIMUM STRESS **9**



ELONGATION AT BREAK **9**

PRINT SETTINGS

Nozzle	230-260°C
Heatbed	50-60°C
Adhesive	not required
Speed	20-40mm/s
Cooling	0-30%

Recommended settings for printers with a 0.4mm Nozzle. Max. 50% layerheight. Optimal print settings may vary between different printers and also depend on environmental factors.

